

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification ⁷ : C08F 10/02, 4/22, 4/02</p>	<p>A1</p>	<p>(11) International Publication Number: WO 00/58375 (43) International Publication Date: 5 October 2000 (05.10.00)</p>
<p>(21) International Application Number: PCT/EP00/02279 (22) International Filing Date: 14 March 2000 (14.03.00) (30) Priority Data: 99106376.9 29 March 1999 (29.03.99) EP (71) Applicant (for all designated States except US): FINA RESEARCH S.A. [BE/BE]; Zone Industrielle C, B-7181 Seneffe (Feluy) (BE). (72) Inventors; and (75) Inventors/Applicants (for US only): DEBRAS, Guy [BE/BE]; Rue Champ de la Chapelle 12, B-6210 Frasnes-lez-Gosselies (BE). BODART, Philippe [BE/BE]; Rue aux Granges 108, B-4480 Clermont-sous-Huy (BE). (74) Common Representative: FINA RESEARCH S.A.; Patent Department, Zone Industrielle C, B-7181 Seneffe (Feluy) (BE).</p>		<p>(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published With international search report.</p>
<p>(54) Title: PRODUCTION OF POLYETHYLENE (57) Abstract A process for producing a polyethylene resin having a monomodal molecular weight distribution in a single polymerisation reactor using a chromium-based catalyst system, by copolymerising ethylene and an alpha-olefinic-comonomer having from 3 to 8 carbon atoms, the polyethylene resin comprising a blend of a higher molecular weight fraction polymerised by a first chromium-based catalyst of the system and a lower molecular weight fraction polymerised by a second chromium-based catalyst of the system, wherein the comonomer incorporation in the higher molecular weight fraction is greater than the comonomer incorporation in the lower molecular weight fraction is greater than the comonomer incorporation in the lower molecular weight fraction whereby the higher and lower molecular weight fractions differ in density by from 0.01 to 0.03g/cc.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

PRODUCTION OF POLYETHYLENE

The present invention relates to a process for producing polyethylene in particular having improved mechanical properties.

Polyethylene is known for use in the manufacture of a wide variety of articles. The polyethylene polymerisation process can be varied in a number of respects to produce a wide variety of resultant polyethylene resins having different physical properties which render the various resins suitable for use in different applications. In particular, it is known to use polyethylene for use in applications where the polyethylene is required to have crack resistance, both resistance to rapid and to slow crack growth. For example, polyethylene is known for use in the manufacture of pipes where it is required that the material of the pipe has sufficient crack resistance so as to avoid inadvertent fracture in service. Polyethylene is also used for blow moulding and for the manufacture of films. For such applications the polyethylene is also required to have good mechanical properties, such as impact resistance, tear strength and environmental stress cracking resistance (ESCR).

Chromium-based catalysts used for the production of polyethylene have been known for some time. Typically, for the manufacture of polyethylene used as a pipe resin, the polyethylene is polymerised in a reactor using a chromium-based catalyst to product a monomodal molecular weight distribution of the resultant polyethylene resin.

It is known in the art that the physical properties, in particular the mechanical properties, of a polyethylene product can vary depending on what catalytic system was employed to make

the polyethylene. This is because different catalyst systems tend to yield different molecular weight distributions in the polyethylene produced.

EP-A-0647661 discloses chromium catalyst compositions and polymerisation processes therewith. The catalyst compositions comprise at least two chromium catalyst systems which have different supports having different pore volumes and surface areas. It is disclosed that the resins produced are useful for film applications. The specification does not address the problem of the production of polyethylene having crack resistance for use in the manufacture of pipes.

WO-A-98/18554 discloses a process for the polymerisation of alpha-olefins using an aluminophosphate support.

EP-A-0591968 discloses chromium catalyst compositions for use in polymerising olefins to produce polyethylene copolymers having good environmental stress crack resistance. Like EP-A-0647661, the chromium catalyst composition comprises at least two chromium catalyst systems having respective supports with different average pore radius. That difference is sufficient preferentially to introduce a non-ethylene comonomer into the higher molecular weight portion of the resulting copolymer. Like EP-A-0647661, EP-A-0591968 does not address the production of polyethylenes having crack resistance for use in the manufacture of pipes.

EP-A-0849293 discloses the production of polyethylene having a bimodal molecular weight distribution.

EP-A-0166157 discloses silicon and/or fluorine treated alumina for use in the production of olefin polymers having high density and ultra high molecular weight.

The present invention aims in one aspect to provide a process for producing polyethylene, in particular a polyethylene having a monomodal molecular weight distribution, having improved mechanical properties.

Accordingly, the present invention provides a process for producing a polyethylene resin having a monomodal molecular weight distribution in a single polymerisation reactor using a chromium-based catalyst system, by copolymerising ethylene and an alpha-olefinic-comonomer having from 3 to 8 carbon atoms, the polyethylene resin comprising a blend of a higher molecular weight fraction polymerised by a first chromium-based catalyst of the system and a lower molecular weight fraction polymerised by a second chromium-based catalyst of the system, wherein the comonomer incorporation in the higher molecular weight fraction is greater than the comonomer incorporation in the lower molecular weight fraction whereby the higher and lower molecular weight fractions differ in density by from 0.01 to 0.03g/cc.

The first and second catalysts may be differently treated portions of the same catalyst and physically blended before activation of the catalysts. Alternatively, the first and second catalysts may be different catalysts and physically blended before or after activation of the catalysts.

The present inventor has discovered surprisingly that by producing a polyethylene resin having a monomodal distribution using a single reactor but with two catalysts improved mechanical properties can be achieved by providing that the catalysts achieve greater comonomer incorporation in the higher molecular weight fraction than in the lower molecular weight fraction.

Embodiments of the present invention will now be described by way of example only with reference to the accompanying drawings, in which:-

Figures 1 and 2 are each gel permeation chromatographs of respective polyethylene resins using different catalysts for blending to produce a catalyst system for use in the present invention; and

Figure 3 is a gel permeation chromatograph of a monomodal polyethylene resin produced in accordance with the invention.

In accordance with the invention, a monomodal polyethylene resin is produced in one reactor using a pair of chromium-based catalysts forming a composite catalyst system. The pair of catalysts is selected so that one catalyst of the pair produces a higher molecular weight fraction of the monomodal polyethylene resin and the other catalyst of the pair produces a lower molecular weight fraction thereof. Moreover, the catalysts of the pair are selected so that the catalyst producing the high molecular weight fraction also incorporates a greater amount of comonomer into that fraction than the amount of comonomer incorporated into the lower molecular weight fraction by the other catalyst of the pair. In this way, in the resultant resin, which has a monomodal molecular weight distribution resulting from the combined molecular weight distributions of the two fractions, there is a high level of comonomer incorporation in the high molecular weight part. Thus the higher and lower molecular weight fractions produce respectively lower and higher density fractions in the ultimate polyethylene resin. The high molecular weight fraction can have a relatively narrow molecular weight distribution compared to that of the lower molecular weight fraction. There is a separation between the peaks of the higher and lower molecular weight distributions, although the combined distribution is monomodal. This in turn leads to improved mechanical properties of the resultant resin.

In one preferred embodiment, the chromium-based catalyst system comprises a physical blend of two chromium-based catalysts which have been blended before activation. The two catalysts are essentially the same catalysts, but one catalyst has been pretreated, for example by fluorination, in such a way as to alter the degree of comonomer incorporation in the fraction produced by that catalyst. For example, the catalyst system may comprise as a first chromium-based catalyst of the system, a fluorinated version of a chromium-based catalyst having a high degree of comonomer incorporation in a higher molecular fraction having a narrow molecular weight distribution, and an unfluorinated version of the same catalyst which would tend to produce a lower molecular weight fraction having a lower degree of comonomer incorporation. In order to decrease the molecular weight the second catalyst can be modified, e.g. by titanation.

Preferably in this embodiment each of the two chromium-based catalysts comprises a supported chromium oxide catalyst having a silica-containing support, for example a silica support or a composite silica and titania support. A particularly preferred chromium-based catalyst may comprise from 0.5 to 5wt% chromium, preferably around 1wt% chromium, based on the weight of the chromium-containing catalyst. When the support includes titanium, the support preferably comprises at least 2wt% titanium, preferably around 2 to 3wt% titanium, based on the weight of the chromium containing catalyst. The untreated chromium-based catalyst may have a specific surface area of from 200 to 700m²/g, preferably from 400 to 550m²/g and a volume porosity of greater than 2cc/g preferably from 2 to 3cc/g.

A particularly preferred chromium-based catalyst for use in this preferred embodiment of the present invention comprises a catalyst having an average pore radius of 190Å, a pore volume of around 2.1cc/g, a specific surface area of around 510m²/g and a

chromium content of around 0.9wt% based on the weight of the chromium-containing catalyst. The support comprises a composite silica and titania support. The amount of titania in the support provides that the catalyst as a whole comprises around 2.3wt% titanium.

The catalyst system of this embodiment comprises a physical mixture of the catalyst in unfluorinated form and the catalyst in fluorinated form. The fluorinated form may be commercially available. Alternatively, the fluorinated form may be produced by fluorination of the unfluorinated catalyst. In a typical fluorination process, the chromium-based catalyst is impregnated with a solution of a fluorine-containing compound, such as ammonium hexafluorosilicate. Typically, from 0.5 to 2wt% fluorine, most typically around 1wt% fluorine, based on the weight of the chromium-based catalyst, is introduced into the catalyst.

The fluorinated version of the catalyst yields higher comonomer incorporation into the polyethylene resin and results in the production of a relatively higher molecular portion having a narrow molecular weight distribution as compared to the polyethylene fraction catalysed by the unfluorinated version of the catalyst.

The two catalysts are physically blended prior to activation in which the catalyst is subjected to an activation step in air at an elevated activation temperature. The activation temperature preferably ranges from 500 to 850°C, more preferably 600 to 750°C.

In a second preferred embodiment, the chromium-based catalyst system comprises a physical blend of two different chromium-based catalysts which have been blended before activation. In contrast

to the first embodiment, the two catalysts are different catalysts. For example, the catalyst to produce the relatively low molecular weight fraction may be a chromium-based catalyst having a relatively low pore volume support and having been titanated so as to deposit titanium on the support, whereas the catalyst to produce the relatively high molecular weight fraction may be a chromium-based catalyst having a support with a relatively high pore volume. Moreover, the catalyst to produce the relatively high molecular weight fraction may have been pretreated, for example by fluorination, so as to increase the degree of comonomer incorporation in the fraction produced by that catalyst.

In this embodiment, the catalyst to produce the lower molecular weight fraction may comprise a supported chromium-oxide catalyst having a silica-containing support, for example a silica support or a composite silica and titania support. A particularly preferred chromium-based catalyst may comprise from 0.5 to 5wt% chromium, preferably around 1wt% chromium, based on the weight of the chromium-containing catalyst. When the support comprises titanium, the support preferably comprises at least 2wt% titanium, preferably around 2 to 5wt% titanium, based on the weight of the chromium-containing catalyst. The chromium-based catalyst may have a specific surface area of from 300 to 700m²/g, preferably from 300 to 500m²/g and a volume porosity of less than 2cc/g, preferably from 1 to 1.6cc/g.

The first catalyst to produce the low molecular weight fraction may have been titanated prior to activation. In the titanation process, the chromium-based catalyst is introduced into an activator and titanated at a temperature of at least 150°C but more preferably around 300°C in an atmosphere of dry, inert gas, for example nitrogen, containing a titanium compound of the general formula selected from $R_nTi(OR')_m$ and $(RO)_nTi(OR')_m$

wherein R and R' are the same or different and are a hydrocarbyl group containing from 1 to 12 carbon atoms, n is 0 to 3, m is 1 to 4 and m+n equals 4, to form a titanated chromium-based catalyst having a titanium content of from 1 to 5 % by weight, more preferably from 2 to 4% by weight based on the weight of the titanated catalyst. Preferably, the titanation compound is a titanium tetraalkoxide, most preferably titanium tetraisopropoxide. Preferably, the titanation step is preceded by a dehydration step in which the catalyst is heated at a temperature of at least 300°C in an atmosphere of dry, inert gas, preferably nitrogen, so as to remove physically adsorbed water therefrom.

After the titanation treatment, the second catalyst for producing the high molecular weight fraction is added to the activator and both catalysts are activated at a high temperature under air, for example a temperature of from 500 to 900°C, typically around 600°C.

The second catalyst in this embodiment may comprise a supported chromium-oxide catalyst having a silica-containing support, for example a silica support or a composite silica and titania support. A particularly preferred chromium-based catalyst may comprise from 0.5 to 5wt% chromium, preferably around 1wt% chromium, based on the weight of the chromium-containing catalyst. When the support comprises titanium, the support preferably comprises at least 2wt% titanium, preferably around 2 to 4wt% titanium, based on the weight of the chromium-containing catalyst. The chromium-based catalyst may have a specific surface area of from 300 to 700m²/g, preferably from 400 to 550m²/g and a volume porosity of from 1.5 to 2.5cc/g. The second catalyst may have been modified with fluorine (as described above) prior to its introduction into the reactor.

In a third embodiment of the present invention, the catalyst

comprises, as for the second embodiment, different catalysts which have additionally been differently treated after respective activation thereof in air at high temperature e.g. greater than 600°C. For example, the first catalyst may comprise a chromium-based catalyst having a low pore volume support and the second chromium-based catalyst may have a high pore volume support. Moreover, the first catalyst may comprise a support of for example aluminium phosphate (AlPO_4) which may have been chemically reduced (e.g. by carbon monoxide) at high temperature and re-oxidised. The second catalyst may have a silica-containing support which has been subjected to fluorination as for the first embodiment with subsequent chemical reduction, for example by carbon monoxide.

The first catalyst may be reduced or re-oxidised by the following process - the catalyst is heated to a temperature of around 850°C and carbon monoxide in nitrogen is passed thereover for a period of 2 hours, and then the catalyst is heated in air at a temperature of 750°C for a period of 2 hours.

The second catalyst may have been fluorinated using the process described hereinabove with respect to the first embodiment, with subsequent carbon monoxide reduction. In the carbon monoxide reduction step, the chromium-based catalyst is subjected to a chemical reduction process in which at least a portion of the chromium is reduced to a low valence state. Preferably, the chromium-based catalyst is reduced in an atmosphere of dry carbon monoxide at a temperature of from 250 to 500°C, more preferably 350 to 450°C, and most preferably at a temperature of around 370°C.

The second catalyst can be a Cr/silica, a Cr/silica-titania; or a Cr/ silica-alumina catalyst. If the support includes Ti, the

Ti content may vary from 2 to 5wt%. If the support includes alumina, the Al content may be up to 4wt%, preferably around 2wt%. The pore volume is typically larger than 1.5ml/g, more preferably larger than 2ml/g, and the surface area is typically larger than 400m²/g.

Prior to loading into the reactor, both catalysts can be precontacted with specific metal alkyl cocatalysts to further modify the melt index of each fraction and enhance comonomer incorporation.

In the polymerisation reactor, ethylene monomer and an alpha-olefinic comonomer comprising from 3 to 8 carbon atoms are fed thereinto in the liquid phase, typically in an inert diluent, preferably isobutane, together with the composite chromium-based catalyst system. Typically, the copolymerisation is performed at a temperature of from 90 to 105°C, more typically from 95°C to 100°C, and at a pressure of from 20 to 60 bars, more typically around 42 bars. The comonomer preferably comprises 1-hexene, but may alternatively comprise 1-butene, 1-pentene, 4-methyl 1-pentene, 1-heptene or 1-octene or a mixture thereof.

Typically, the ethylene monomer comprises from 3 to 8% by weight and the comonomer comprises from 0.2 to 4% by weight, each based on the total weight of the monomer and comonomer in the inert diluent. A typical starting composition comprises an ethylene concentration of around 6wt% and a 1-hexene concentration of around 1.5wt% both in isobutane as inert diluent.

In the polymerisation reactor, polyethylene is produced by copolymerisation of the ethylene and the 1-hexene. In accordance with the preferred process, the process variables such as the ethylene and comonomer flow rate and the temperature are controlled so as to produce a polyethylene resin having a

specified high load melt index (HLMI) yielding the required mechanical properties of the resin. Typically, the HLMI ranges from 2 to 40g/10min, and is most typically from 9 to 30g/10min.

The melt index MI_2 and the high load melt index HLMI are determined using the procedures of ASTM D1238 using respective loads of 2.16kg and 21.6kg at a temperature of 190°C. The HLMI is broadly inversely indicative of the molecular weight of the polymer. In other words, a low melt index is indicative of a high molecular weight for the polyethylene, and vice versa. The density of the resultant polyethylene is controlled by varying the amount of comonomer fed to the polymerisation reactor.

The resultant polyethylene resin has a monomodal molecular weight distribution.

As is known in the art, a monomodal molecular weight distribution has a single peak in the gel permeation chromatography curve of the resin. The two fractions are combined to form a composite resin having a monomodal molecular weight distribution, and the difference between the HLMI values of the two fractions is controlled so that, for any combination of resins produced in accordance with the invention, the resultant molecular weight distribution is nevertheless monomodal. The density of the two resin products produced in the first and second reactors may differ substantially, i.e. from 0.01 to 0.03g/cc yet still providing a monomodal molecular weight distribution in the final combined resin. Such a density difference may yield improved slow crack growth resistance of the combined resin. A typical density difference is around 0.02g/cc.

The density of the combined polyethylene is from 0.930 to 0.960g/cc, preferably from 0.937 to 0.950g/cc.

Without being bound by theory, it is believed that the higher

degree of introduction of the comonomer into the polymer chains in the high molecular weight fraction as compared to the low molecular weight fraction leads to a change in the mechanical properties of the resultant polyethylene resin which in turn can yield an increase in the slow crack resistance and in the rapid crack propagation resistance of the polyethylene resin when used for the manufacture of pipes.

The present invention will now be described with reference to the following non-limiting Examples.

EXAMPLE 1

In this Example, two different chromium-based catalysts were physically blended, after the respective activation of each catalyst, to form a composite chromium-based catalyst system which was employed in a process to produce polyethylene resin having a monomodal molecular weight distribution.

In this Example, the composite chromium-based catalyst system comprises a first catalyst for producing a low molecular weight fraction, the first catalyst having a low degree of comonomer incorporation, which had been reduced and reoxidised, subjected to titanation and then activated at high temperatures and the second catalyst, for forming a high molecular weight fraction, had a high pore volume, had been activated at a low activation temperature, had been fluorinated and then subjected to reduction by carbon monoxide. In addition, the second catalyst had been precontacted with a cocatalyst.

The first catalyst, for producing the relatively low molecular weight fraction of the composite resin, comprised an aluminium phosphate (AlPO_4) based chromium oxide catalyst having the pore

volume, surface area, phosphorous/aluminium atomic ratio and chromium content as specified in Table 1. This catalyst ("Catalyst A") was activated in air at a temperature of around 750°C and was thereafter subjected to a chemical reduction and reoxidation process. In the reduction step, the catalyst was chemically reduced by carbon monoxide at a temperature of around 850°C, and the catalyst was thereafter re-oxidised in air at a temperature of around 750°C.

The catalyst for producing the relatively high molecular weight fraction ("Catalyst B") comprised a chromium-based catalyst having a silica-titania support with chromium oxide deposited thereon. The catalyst had the pore volume, surface area, titanium content (on the support) and chromium content as specified in Table 1. The catalyst was activated at 650°C in the presence of fluorine (1.4wt% NH_4BF_4) to yield a fluorine content of 1wt% based on the weight of the catalyst. Following the activation step, the catalyst was chemically reduced by dry carbon monoxide at a temperature of around 370°C.

Before catalyst A and catalyst B were combined, each catalyst was pre-contacted with a co-catalyst, which in this Example comprised a metal alkyl. Thus catalyst A was pre-contacted with triethylboron (TEB) (4ppm in the diluent) and catalyst B was pre-contacted with 4 ppm triisobutyl aluminium (TIBAl) (4ppm in the diluent).

In order to demonstrate the nature of the polyethylene resin fraction produced by each of catalysts A and B, each of the two catalysts A and B were individually employed on the presence of the respective co-catalyst as specified above to produce a polyethylene resin under the respective conditions specified in Table 1. Thus catalyst A was employed to produce a polyethylene

copolymer at a polymerisation temperature of around 95°C wherein the ethylene monomer comprised 6wt%, and the comonomer, being 1-hexene, comprised 1.5wt%, each based on the weight of the diluent which comprised isobutane.

Catalyst B was individually employed under similar conditions and the polyethylene resins produced by the respective catalysts were recovered and the properties determined as specified in Table 1.

Gel phase chromatographs for each of the two polyethylene resins recovered were measured for catalysts A and B and these are shown in Figures 1 and 2 respectively.

It may be seen that catalyst A produced a polyethylene resin of relatively low molecular weight (i.e. a value of Mw of around 118,000), as compared to that produced by catalyst B, (which had a value of Mw of 244,000). The density of the resin produced by catalyst B was lower than that produced by catalyst A, indicating a higher degree of comonomer incorporation into the higher molecular weight resin. The resin produced by catalyst A had a melt index MI₂ of 5.6g/10min, whereas the resin produced by catalyst B had an HLMI of 6.3g/10min.

It may be seen from Figures 1 and 2 that the resin produced by catalyst A has a peak at a molecular weight value lower than that for the resin produced by catalyst B.

In accordance with the process of the invention, the two catalysts A and B, but without their respective co-catalysts as specified above, were combined and introduced into a single polymerisation reactor and were thereafter employed to produce a polyethylene resin copolymer under the conditions specified in Table 1. The properties of the resultant polyethylene resin are specified in Table 1. It may be seen that the resin had an HLMI

of around 25g/10min and a density of around 0.947g/cc. The gel phase chromatograph of the resin produced in accordance with Example 1 is illustrated in Figure 3. It may be seen that curve A, which represents the molecular weight distribution of the polyethylene resin, is monomodal. Curves B and C represent the molecular weight distributions of the two fractions produced by catalysts A and B, these curves corresponding respectively to the curves shown in Figures 1 and 2. Lines D and E on Figure 3 represent the comonomer distribution for each of curves B and C respectively. It may be seen that the comonomer distribution is higher for the higher molecular weight fraction than for the lower molecular weight fraction.

EXAMPLE 2

In this Example, the composite chromium-based catalyst comprised a mixture of a first chromium-based catalyst (catalyst C) which had been titanated in situ and a second chromium-based catalyst which had a higher degree of comonomer incorporation as a result of having a higher pore volume, having been fluorinated in situ and having been activated at a higher activation temperature.

In a manner similar to that for Example 1, each of catalysts C and D, having the catalyst properties and activation conditions specified in Table 2, was individually employed to polymerise ethylene under conditions specified in Table 2 to yield a respective (the operating) polyethylene having the properties specified in Table 2. In addition, in accordance with Example 2, a composite catalyst comprising a mixture of catalysts C and D was employed to polymerise ethylene under the operating conditions specified in Table 2, to yield a polyethylene resin having the properties specified in Table 2.

The first catalyst, catalyst C, comprised a chromium-based

catalyst on a silica support having relatively low pore volume and relatively low surface area whereas the second catalyst, catalyst D, also comprised a chromium-based catalyst on a silica support and had a relatively high pore volume and a relatively high surface area. The first catalyst, catalyst C, was subjected to titanation during which 4wt% titanium was introduced into the catalyst by drying the catalyst to 300°C then titanating the catalyst with titanium isopropoxide. Thereafter, the titanated catalyst was actuated by being held at a temperature of 650°C in air for 6 hours. In contrast, the second catalyst, catalyst D, was simply subjected to activation in air at a temperature of 650°C.

In forming the mixture of catalysts C and D for Example 2, an amount of catalyst C was titanated to an amount of 4wt% titanium in the manner specified above. Then, catalyst D was added and thereafter the composite catalyst was activated in air at a temperature of 650°C.

It will be seen from Table 2 that again the density of the resin produced using catalyst D is lower than that produced using catalyst C, indicating a higher degree of comonomer incorporation into the high molecular weight resin fraction produced by catalyst D.

TABLE 1

	Catalyst A	Catalyst B	Example 1
<u>CATALYST</u>	Cr/Al PO ₄	Cr/SiO ₂ -TiO ₂	
Pore Volume (cc/g)	1.0	2.3	
Surface Area (m ² /g)	190	543	
P/Al Atomic Ratio	0.68	-	
Ti (wt%)	-	2.6	
Cr (wt%)	1.0	1.0	
<u>ACTIVATION CONDITIONS</u>			
Activation T(C°)	750	650	
Added Fluorine (wt%)	-	1.4	
CO reduction T(C°)	850	370	
Reoxidation T(C°)	750	-	
<u>OPERATING CONDITIONS</u>			
Polymerisation T(C°)	95	95	95
C ₂ (wt%)	6	6	6
C ₆ (wt%)	1.5	1.5	1.5
Co-catalyst			
Type	TEB	TEAL	-
ppm	4	4	-
<u>POLYETHYLENE PROPERTIES</u>			
MI ₂ (g/10')	5.6	-	-
HLMI (g/10')	-	6.3	25
Density (g/cc)	0.9547	0.936	0.947
Mn (kDa)	8	19	11
Mw (kDa)	118	244	201
Mz (kDa)	2257	2465	2400
D	14.8	12.4	18

TABLE 2

	Catalyst C	Catalyst D	Example 2
<u>CATALYST</u>	Cr/SiO ₂	Cr/SiO ₂	
Pore Volume (cc/g)	1.5	3	
Surface Area (m ² /g)	300	500	
Ti (wt%)	4.0	-	
Cr (wt%)	1.0	1.0	
<u>ACTIVATION CONDITIONS</u>			
Activation T(C°)	650	650	
Added Fluorine (wt%)	-	-	
CO reduction T(C°)	-	-	
Reoxidation T(C°)	-	-	
<u>OPERATING CONDITIONS</u>			
Polymerisation T(C°)	100	100	100
C ₂ (wt%)	6	6	6
C ₆ (wt%)	0.2	0.2	0.2
Co-catalyst			
Type	-	-	-
ppm	-	-	-
<u>POLYETHYLENE PROPERTIES</u>			
MI ₂ (g/10')	0.5	0.05	-
HLMI (g/10')	68.2	5.9	20
Density (g/cc)	0.955	0.944	0.950
Mw (kDa)	151	288	211
D	15.8	15.7	16

CLAIMS:

1. A process for producing a polyethylene resin having a monomodal molecular weight distribution in a single polymerisation reactor using a chromium-based catalyst system, by copolymerising ethylene and an alpha-olefinic-comonomer having from 3 to 8 carbon atoms, the polyethylene resin comprising a blend of a higher molecular weight fraction polymerised by a first chromium-based catalyst of the system and a lower molecular weight fraction polymerised by a second chromium-based catalyst of the system, wherein the comonomer incorporation in the higher molecular weight fraction is greater than the comonomer incorporation in the lower molecular weight fraction whereby the higher and lower molecular weight fractions differ in density by from 0.01 to 0.03g/cc.
2. A process according to claim 1 wherein the first and second chromium-based catalysts comprise a common catalyst and at least one of the first or second chromium-based catalysts has been pre-treated so as to vary the molecular weight distribution of the resin fraction produced by that catalyst with respect to the other catalyst.
3. A process according to claim 2 wherein the pre-treatment comprises fluorination.
4. A process according to claim 2 or claim 3 wherein the first and second chromium-based catalysts are physically blended prior to a common activation step.
5. A process according to claim 1 wherein the first and second chromium-based catalysts comprise different catalysts.
6. A process according to claim 5 wherein the first and second

chromium-based catalysts include supports having different pore volumes.

7. A process according to claim 5 or claim 6 wherein at least one of the first and second chromium-based catalysts has been pre-treated so as to vary the molecular weight distribution of the resin fraction produced by that catalyst with respect to the other catalyst.

8. A process according to claim 7 wherein the first catalyst has been fluorinated in a pre-treatment step.

9. A process according to claim 7 or claim 8 wherein the second chromium-based catalyst has been titanated prior to activation.

10. A process according to any one of claims 5 to 9 wherein the first and second chromium-based catalysts are physically blended prior to a common activation step.

11. A process according to claim 5 wherein the first and second chromium-based catalysts have supports having different chemical compositions.

12. A process according to claim 11 wherein the first chromium-based catalyst has a silica-containing support and a second chromium-based catalyst has a phosphate-containing support.

13. A process according to claim 12 wherein the silica-containing support has been fluorinated and chemically reduced after activation thereof.

14. A process according to claim 12 wherein the second chromium-based catalyst has been subjected to a chemical reduction and reoxidation process after activation thereof.

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/EP 00/02279

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C08F10/02 C08F4/22 C08F4/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 647 661 A (PHILLIPS PETROLEUM CO) 12 April 1995 (1995-04-12) cited in the application	1-11
Y	the whole document page 4, line 34 - line 36; claims; examples	12-14
Y	WO 98 18554 A (CHEVRON CHEM CO) 7 May 1998 (1998-05-07) cited in the application page 8, line 3 - line 5 claims	12-14
X	EP 0 591 968 A (PHILLIPS PETROLEUM CO) 13 April 1994 (1994-04-13) cited in the application	1-11
Y	the whole document	12-14
	-/--	

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"8" document member of the same patent family

Date of the actual completion of the international search

27 June 2000

Date of mailing of the international search report

06/07/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Kaumann, E

INTERNATIONAL SEARCH REPORT

Inter. Appl. No.

PCT/EP 00/02279

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 849 293 A (FINA RESEARCH) 24 June 1998 (1998-06-24) cited in the application claims ---	1-14
A	EP 0 166 157 A (PHILLIPS PETROLEUM CO) 2 January 1986 (1986-01-02) cited in the application the whole document -----	1-14

INTERNATIONAL SEARCH REPORT

information on patent family members

International Application No

PCT/EP 00/02279

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0647661 A	12-04-1995	US 5508362 A	16-04-1996
		AU 663656 B	12-10-1995
		AU 6887594 A	27-04-1995
		CA 2124732 A,C	09-04-1995
		CN 1106024 A,B	02-08-1995
		CN 1152581 A	25-06-1997
		DE 69409055 D	23-04-1998
		DE 69409055 T	02-07-1998
		ES 2113593 T	01-05-1998
		FI 944700 A	09-04-1995
		HU 70080 A,B	28-09-1995
		JP 7188324 A	25-07-1995
		NO 943812 A	10-04-1995
		TR 28158 A	13-02-1996
		US 5654249 A	05-08-1997
		ZA 9405476 A	06-03-1995
WO 9818554 A	07-05-1998	US 5869587 A	09-02-1999
		AU 5159198 A	22-05-1998
		US 6043181 A	28-03-2000
EP 0591968 A	13-04-1994	US 5486584 A	23-01-1996
		AT 155146 T	15-07-1997
		AU 654445 B	03-11-1994
		AU 4628793 A	21-04-1994
		CA 2100144 A	09-04-1994
		CN 1085566 A,B	20-04-1994
		CN 1150954 A	04-06-1997
		CN 1167121 A	10-12-1997
		DE 69312005 D	14-08-1997
		DE 69312005 T	30-10-1997
		DK 591968 T	26-01-1998
		ES 2104017 T	01-10-1997
		HU 69750 A,B	28-09-1995
		JP 6199920 A	19-07-1994
		MX 9306146 A	29-04-1994
		NO 933577 A	11-04-1994
		SG 48772 A	18-05-1998
		US 5595953 A	21-01-1997
EP 0849293 A	24-06-1998	WO 9828349 A	02-07-1998
		EP 0946612 A	06-10-1999
		US 6015866 A	18-01-2000
EP 0166157 A	02-01-1986	US 4806513 A	21-02-1989
		AT 94151 T	15-09-1993
		CA 1251894 A	28-03-1989
		DE 3587567 D	14-10-1993
		DE 3587567 T	05-01-1994
		ES 543553 D	16-07-1986
		ES 8609177 A	16-12-1986
		ES 552105 D	01-09-1987
		ES 8707978 A	16-11-1987
		HU 38559 A,B	30-06-1986
		JP 2115390 C	06-12-1996
		JP 8005934 B	24-01-1996
		JP 60258210 A	20-12-1985
		KR 9302229 B	27-03-1993

INTERNATIONAL SEARCH REPORT

information on patent family members

International Application No

PCT/EP 00/02279

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0166157 A		NO 852138 A,B,	02-12-1985
		US 5037911 A	06-08-1991
		US 5401820 A	28-03-1995
